


SAFECO SAS
172 AVENUE DE L'EUROPE 13760- SAINT CANNAT FRANCE

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Knitted fabric (FESTIEVENT)
Composition : (A)100%p
Sample Receiving Date : Jul 15, 2025
Testing Period : Jul 16, 2025 - Jul 30, 2025
Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).
Test Performed : Selected test(s) as requested by applicant

Conclusion	A	Remark
Classification In Category M1	See Results	

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Hangzhou Branch



jack-yl_zhang(Account Executive)



Test Result

Flammability test ^

I. Test conducted

This test was conducted according to NF P 92-507:2004 Fire safety - building-interior fitting materials - Classification according to their reaction, and the test methods as following:

1. NF P 92-503:1995 Safety against fire - Building materials - Reaction to fire tests Electrical burner test used for flexible materials.
2. NF P 92-504:1995 Safety against fire - Building materials - Reaction to fire tests - Flame persistence test and speed of the spread of flame.

II. Sample details

Sample description	Fabric
Color	White
Area density	163 g/m ²
Specimen size	600 mm × 180 mm (NF P 92-503) 460 mm × 230 mm (NF P 92-504)

III. Conditioning

Prior to testing, the sample was conditioned in an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5% for 7 days or until constant mass is obtained.

IV. Test results

i) NF P 92-503:1995 Electrical burner test

Face, Length

During the testing, the following details are noted	1	2	3	4	Average
Hole (Yes/No)	Yes	Yes	Yes	Yes	
Applied time (s)	20	20	20	20	
Max. afterflame time after withdrawal the pilot flame (s)	0	0	0	0	0
Afterglow time (s)	0	0	0	0	0
Flaming molten droplets (Yes/No)	No	No	No	No	
Non-flaming molten droplets (Yes/No)	No	No	No	No	
Flaming debris (Yes/No)	No	No	No	No	
Non-flaming debris (Yes/No)	No	No	No	No	
White-hot spots with propagation effects (Yes/No)	No	No	No	No	



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 1/F., Building 6 & 3-6/F., Building 4, No.1180, Bin'an Road, Changhe Street, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571) 86791199 www.sgs.com.cn
 中国·浙江·杭州市滨江区长河街道滨安路1180号4幢3-6层、6幢1层 邮编: 310052 t (86-571) 86791199 sgs.china@sgs.com

After testing, the following details are noted	1	2	3	4
Max. destruction length from the lower edge (mm)	110	105	105	105
Average destruction length (mm)	106.3			
Max. width of the destroyed zones between 450mm and 600mm from the test piece lower edge (mm)	0	0	0	0
Average destroyed width (mm)	0			

ii) NF P 92-504:1995 Flame persistence test

Face, Length

Ignition time	After-flame time (s)	Flaming Drops (Yes/No)	Non-flaming Drops (Yes/No)	Ignition times	After-flame time (s)	Flaming Drops (Yes/No)	Non-flaming Drops (Yes/No)
1	0	No	No	16	0	No	No
2	0	No	No	17	0	No	No
3	0	No	No	18	0	No	No
4	0	No	No	19	0	No	No
5	0	No	No	20	0	No	No
6	0	No	No	21	0	No	No
7	0	No	No	22	0	No	No
8	0	No	No	23	0	No	No
9	0	No	No	24	0	No	No
10	0	No	No	25	0	No	No
11	0	No	No	26	0	No	No
12	0	No	No	27	0	No	No
13	0	No	No	28	0	No	No
14	0	No	No	29	0	No	No
15	0	No	No	30	0	No	No

Number of tested specimens: 4



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1/F., Building 6 & 3-6/F., Building 4, No.1180, Bin'an Road, Changhe Street, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571) 86791199 www.sgsgroup.com.cn
 中国·浙江·杭州市滨江区长河街道滨安路1180号4幢3-6层、6幢1层 邮编: 310052 t (86-571) 86791199 sgs.china@sgs.com

Annex I, Requirements

Table 1 Resume of classification for flexible materials which thickness no more than 5mm

Test Items	Criteria of classification				
Test for hot melt materials		Not ignite the wadding	Not ignite the wadding	Ignite the wadding	Ignite the wadding
Electrical Burner Test ^{a)}	No drops	Non-flaming molten droplets	Flaming drops or debris	Non-flaming molten droplets	Flaming drops or debris
Inflammation ≤ 5s	M1	M1	M2	M4	M4
Inflammation > 5s and Average destroyed length <350 mm	M2	M2	M3	M4	M4
Inflammation > 5s and Average destroyed width <90 mm between the 450 mm and 600 mm in length	M3	M3	M4	M4	M4
Flame Spread Test (flame spread <2 mm/s)			M4	M4	M4

a) If the materials presented a particular behaviour, the classification also need to refer to Table 3.
The details of classification M0 refer to clause 3.3 of NF P 92-507:2004.

Table 3 Resume of classification for the materials presented a particular behaviour

Test Items	Criteria of classification				
Test for hot melt materials		Not ignite the wadding	Not ignite the wadding	Ignite the wadding	Ignite the wadding
Flame Persistence Test	No drops	Non-flaming molten drops	Flaming drops or debris	Non-flaming molten drops	Flaming drops or debris
Flame persistence time≤2s	M1	M1	M2	M4	M4
Flame persistence time≤5s	M2	M2	M3	M4	M4
Flame persistence time >5s and Flame Spread <2 mm/s	M3	M3	M4	M4	M4



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1/F., Building 6 & 3-6/F., Building 4, No.1180, Bin'an Road, Changhe Street, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571) 86791199 www.sgs.com.cn
 中国·浙江·杭州市滨江区长河街道滨安路1180号4幢3-6层、6幢1层 邮编: 310052 t (86-571) 86791199 sgs.china@sgs.com

Statement: This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

^This test was carried out by SGS Anji Laboratory

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.

End of Report

Scan to see the report



SL62506327887301TX

Verification:
check.sgsonline.com.cn

